

9000 NYLON



9002LF
Yellow (GS)

9004LF
Yellow (RS)

9006LF
Orange

9008LF
Red (BS)

9010LF
Purple

9012LF
Violet

9014LF
Blue (RS)

9016LF
Blue (GS)

9018LF
Green



9020LF
Brown

9024LF
FL. Magenta

9026LF
FL. Violet

9028LF
FL. Green

When PANTONE® color matching is key, International Coatings has the solutions. Our Color System series are specifically formulated to provide simulations of the PANTONE® color standards.

Products	Mesh in / cm	Recommendations	Fusing Temp.	Opacity	Bleed Resistance	Squeegee & Edge	Hot Peel Transfer	Cold Peel Transfer	Heat Seal Time & Temp.
9000 Series Nylon Color System	110-305 in or 43-120 cm	Press ready plastisol for printing on light & dark nylon fabrics. Add 900LF Catalyst 16 to 1 by Volume 20 to 1 by Weight	325°F or 163° C	Good	None	Triple / Dual Durometer sharp edge 60-70-60 for dark fabrics. 70-90-70 for light fabrics.	Not Recom- mended	For Caps & Nylon Jerseys use 304 Powder Adhesive	Cold Peel 350°F - 375°F 10-15 seconds