

MULTIPURPOSE DIRECT PRINT OR TRANSFER PLASTISOL



Products	Mesh in / cm	Recommendations	Fusing Temp.	Opacity	Bleed Resistance	Squeegee & Edge	Hot Peel Transfer	Cold Peel Transfer	Heat Seal Time & Temp.
Multipurpose Standard Inks	86-305 in or 34-120 cm	For use on white and light colored 100% cotton fabrics. Best on manual presses.	325°F or 163° C	Good	None	65 - 70 Duro sharp edge	Add Quick Trans 500	Good	Hot Peel 375°F - 400°F 4-7 seconds