



Texisil Auxiliaries

PRODUCT RANGE

CATALYSTS

TEXISIL AUSILIARI Code 166650 Package: 1 and 5 kg	Catalyst. Use % = 7 - 10%: <i>7%: Texisil White 3d, Texisil White Extra, Texisil Matt White, Texisil Opaque Base, Texisil Opaque Matt Base, Texisil Puff Base</i> <i>10%: Texisil Clear Base, Texisil Matt Transparent</i> Pot life (mixture) = 6 - 8 hours Curing temperature = 130°C during 3 minutes <i>Texisil Catalyst is indicated for printing with automatic machines</i>
TEXISIL CATALYST SUPER FAST Code 166654 Package: 1 and 5 kg	Catalyst. Use % = 3 - 5% Pot life (mixture) = up to 3 hours Curing temperature = 90°C during 2-3 minutes <i>Texisil Catalyst Super Fast is indicated for manual printing</i>

THINNERS

TEXISIL THINNER Code 166651 Package: 1 Libro	Thinner. It reduces ink viscosity without compromising the opacity; it is useful for the application of silicone inks when working on multi-colour automatic machines. <ul style="list-style-type: none"> • The maximum use percentage is 5%.
TEXISIL THINNER FAST Code 166652 Package: 1 Libro	Thinner. It reduces ink viscosity without compromising the opacity; it is useful for the application of silicone inks when working on multi-colour automatic machines. It reduces the intermediate drying times with FLASH lamps. <ul style="list-style-type: none"> • The maximum use percentage is 5%.

SPECIAL INSTRUCTIONS

- Always test the printing characteristics, before starting production
- Always check curing conditions. The addition of additives could require different curing temperature and time.

WARNING

This technical data sheet does not replace either the Safety Data Sheet or the specific Conformity Declaration. These documents may be required to our SHEQ (Product safety office), at the following e-mail address: safety@eptainks.com

The technical data sheet does not relieve the printer, who remains the only responsible of the respect of the regulations, the specifications and the related required certifications of the finished items

IMPORTANT NOTE

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us to the suitability of the product for the intended purpose, does so at his own risk.

While we endeavour to ensure that all advice we give about the product is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

EPTAINKS

Phone: 1 800 561 8844

WillOX